

DESCRIPTION:

Metz Sauereisen 89 is a single component, asphaltic mastic. The compound is spray-applied by airless equipment and results in a flexible coating with superior temperature and chemical resistance properties. Metz Sauereisen 89 is recommended when substrate movement from temperature change and other causes will be encountered. It resists acids, alkalis and salts associated with flue gas environments. The product is not recommended for oil, grease and solvents. The product is formulated as an impervious membrane for use under corrosion resistant monolithic linings or acid-resistant brick masonry and on metal or concrete substrates. Metz Sauereisen 89 maintains excellent elasticity and adhesion over a temperature range of -45°C to +145°C.

FEATURES AND BENEFITS:

- Excellent Chemical Resistance
Outstanding chemical resistance to acids and alkalis. Refer Metz Chemical Resistance Chart.
- Long-term Flexibility
Recommended for use from -50°C to +145°C.
- Easy to apply
Can be topcoated after 24 hours.
- Use on Concrete or Steel
Suitable for application as a membrane on steel or concrete substrates.
- Durable
Retains excellent elasticity.
- Waterproof
Very low permeability.
- Quality Accreditation
The management system governing the development and manufacture of this product is proudly ISO9001:2015 certified.

RECOMMENDED:

As a membrane for brick or monolithic linings in -

- Flue gas environments
- Chimneys
- Waste acid collection sumps
- Floors and drains in acid storage areas.

NOT RECOMMENDED:

- Environments subject to oil, grease and solvent exposure.
- Generally not recommended for continuous liquid immersion.

PHYSICAL PROPERTIES: (Typical Values)

Moisture vapour permeability, metric per.m	0.002
Resistance to abrasion by sandblast	excellent
Maximum service temperature	145°C
Solids (by weight)	70%
Flash point, T.O.C., minimum	38°C
Density (approximate)	1.00- 1.07 kg/litre

Physical properties were determined on specimens prepared under laboratory conditions using applicable ASTM procedures. Actual field conditions may vary and yield different results; therefore data are subject to reasonable deviation.

COVERAGE: Theoretical quantities (allow for wastage)

Apply in two approximately equal coats of 1.5mm each, building to a wet film thickness of 3mm. Each 18.9 litre pail will cover approximately 6 sq.m. at the recommended wet film thickness of 3mm. For larger projects a 208L drum is available.

INSTRUCTIONS FOR USE

1. Temperature of Working Area

Maintain a temperature of 10°C-38°C on substrate, Metz Sauereisen 89 material and air during application. Dew point of air must also be monitored and substrate temperature must be maintained at least 3°C above dew point.

2. Surface Preparation

a) Steel

Surfaces should be dry and free of grease, dust, loose rust and scale. Metal surfaces should be abrasive blasted to AS1627:4 Class 2½ minimum. Priming is not required when using Metz Sauereisen 89 over metal surfaces.

b) New Concrete

Surfaces should be free of laitance, oil, grease and other residue. Concrete shall be at least 14 days old, be dry and have attained at least 20MPa compressive strength. All voids should be filled with an approved repair material such as Metz 33EN-Plaster.

c) Old Concrete

Surfaces should be free of oil, grease, water and other contaminants. This can be achieved by chemical cleaning. Sandblast or hydroblast surfaces to remove attacked concrete and obtain a firm surface. Voids should be filled with an approved repair material such as Metz 33EN-Plaster..

3. Installation

Prior to spraying Metz Sauereisen 89, it should be mechanically remixed. Metz Sauereisen 89 should be applied by airless spray equipment. The following airless spray equipment (or equal) is recommended for application of Metz Sauereisen 89 High Temperature Membrane.

Mastic Pump - Graco 56:1 King Piston Primed Airless, Model 236-477. Remove the filter from the surge tank. Other pumps may be suitable depending upon jobsite requirements. Consult Metz for information.

Mastic Gun: Graco HydroMastic Gun airless, Model 206-718.

Gun Tip: Graco Reverse-a-Clean tip 1.1mm orifice, Model GHD-745.

Material hose: 1.8m whip end, 12.5mm ID.

Material hose: up to 15m overall, 19mm ID

Material hose: for 30-45m overall, 25mm ID

Air compressor: 3m³ (100 cu. ft.) per minute at 0.7 MPa (100 lbs psi) minimum.

Metz Sauereisen 89 can also be applied by using trowel/roller. Contact Metz for details.

Store mastic in 15°C to 30°C warehouse for at least 48 hours before spraying. To prevent sagging on vertical surfaces, the required coverage shall be built up in two approximately equal coats. Application should be done with a 50% overlap in a "cross hatch" sequence to reduce the possibility of pin holes and to assure complete coverage. Second coat shall be applied 2-4 hours after first coat.

Metz Sauereisen 89 should be tested for pinholes after a 24 hour cure at 20°C. Consult Metz for recommended equipment. To repair pinholes, lightly sand the surface around the pinholes to break up the film. 89 should then be applied by trowel or spray in a uniform coating.

Clean Up

Equipment clean up is by kerosene or mineral spirits within 1 hour after use and after each day's use.

4. Setting/Curing

Metz Sauereisen 89 cures to a soft, flexible, tack-free film in 1-2 days depending upon temperature humidity and application thickness. Walls can be overcoated when the Metz Sauereisen 89 is still slightly tacky, however care must be taken when walking over still tacky floor areas.

5. Coverage

Each 18.9 litre pail will cover approximately 6sqm at the recommended wet film thickness of 3mm.

6. Shelf Life

Metz Sauereisen 89 has a minimum shelf life of one (1) year when stored in unopened, tightly sealed containers in a dry location at 20°C.

7. Safety Precautions

Metz Sauereisen 89 is combustible. At all times until cured, the mixture must be protected from flame and extreme heat. Do not use near flame, spark or excessive heat. Do not weld or burn on equipment lined with Metz Sauereisen 89.

During application Metz Sauereisen 89 should be used with adequate ventilation. Prolonged and repeated breathing of concentrated vapor is harmful and should be avoided. Provide positive ventilation to avoid collected vapors, especially in low-lying areas.

For full safety precautions refer to the Safety Data Sheet for this product.

Always ensure you have the latest data sheet version, refer www.metz.net.au

1. The customer must comply strictly with the instructions contained in this product data sheet. Metz is not responsible for any advice or variations to this data sheet which are not confirmed in writing.
2. If the customer has a claim against Metz in respect of any product supplied to the customer by Metz whether due to a fault in the product or the negligence or breach of contract by Metz or for any other reason:
 - a) Metz shall not be liable for any loss or damage including consequential loss or damage or loss of profits arising thereby;
 - b) Metz may at its option replace the defective product free of charge to the customer or refund all payments made to it by the buyer in respect of the defective product; and the maximum liability of Metz shall be the cost of replacing the defective product.